

(15)

JP 2005-194294 A 2005.7.21

【表3】

No.	洗浄液の組成 (質量%)										評価結果		
	界面活性剤		錯化剤		アルカリ成分		フッ化物		pH	残渣除去性		防食性	材料ダメージ性 (SiO <sub>2</sub> /SiOC)
	種類	含有量	種類	含有量	種類	含有量	種類	含有量		ヒア底	側面		
実施例	RLM45	0.1	ジウ酸	0.5	MEA	5	HF	1	7.5	◎	◎	◎	◎
"	"	"	"	"	"	"	"	"	10	○	○	◎	◎
比較例	"	"	"	"	"	"	HF	1	10	×	◎	△	◎
"	"	"	"	"	"	"	"	"	8	○	○	△	◎
"	"	"	ジウ酸	0.5	"	"	"	"	2.5	○	○	○	○
実施例	RLM45	0.1	"	"	"	"	NH <sub>4</sub> F	1	7.5	◎	◎	◎	◎
"	"	"	"	"	MEA	1	HF	0.1	9	○	◎	◎	◎
"	"	"	"	"	"	4	"	"	10	○	◎	◎	○
"	"	"	"	"	"	8	"	3	5	○	◎	◎	◎
"	"	"	"	"	"	0.5	NH <sub>4</sub> F	0.1	8	○	◎	◎	◎
"	"	"	"	"	"	0.3	"	1	10	◎	◎	◎	◎
"	"	"	"	0.1	"	12	"	1	7.8	◎	◎	◎	◎
"	"	"	"	3	"	5	HF	1	7.6	○	○	○	◎
"	"	"	クワ酸	0.5	"	4.5	"	"	7.5	○	△	○	◎
"	"	0.01	ジウ酸	0.5	"	5	"	"	7.5	○	△	○	◎
比較例	スルホン酸	0.1	"	"	"	5	"	"	7.3	◎	◎	◎	◎
"	ニトリ系	0.1	"	"	"	5	"	"	7.3	◎	◎	◎	◎
実施例	RLM45	0.1	"	"	2-MAE	5	"	"	7.3	◎	◎	◎	◎
"	"	"	"	"	1-APOL	5	"	"	7.3	◎	◎	◎	◎

【0056】

10

20

30

40